

KE-1871

Product Description

Shin-Etsu's KE-1871 is a fast, single component, heat curing conformal coating that will cure to form a durable and flexible elastomer for protecting electronic components. KE-1871 is suitable for application by selective spray coating, mass coating, and flow coating, making it ideal for coating circuit boards.

Product Features

- High heat resistant
- Fast cure
- Single component
- Heat cure
- Excellent unprimed adhesion to most substrates

Typical Applications

- Coating circuit boards and other electronic components

Typical Properties

Type	Conformal Coating
Cure Type	Addition
One/Two Component	One
Cold Storage	Y
Color	Light Yellow Translucent
Density @ 23C (g/cm ³)	1.01
Viscosity (cps)	900.00
Cure Conditions	30min @ 120C
Working Time	24 Hours
Shore A Hardness	27
Tensile Strength (MPa)	2.20
% Elongation	180
Shear Strength (MPa)	0.20
Volume Resistivity (TΩ·m)	29
Dielectric Strength (kV/mm)	27
Dielectric Constant	2.9 @ 50Hz
Dielectric Dissipation Factor	2.0 x 10 ⁻⁴ @ 50Hz
Thermal Conductivity (W/m·K)	0.20
Usable Temperature Range (C)	-40 to +200

Note: Values are not for specification purposes.

Warranty- The information and data contained herein are believed to be accurate and reliable; however it is the user's responsibility to determine suitability of use. Since Shin-Etsu Silicones, Inc. cannot know all of the uses to which its products may be put or the conditions of use, it makes no warranties concerning the fitness or suitability of its products for a particular use or purpose. You should thoroughly test any proposed use of our products and independently conclude satisfactory performance in your application. Likewise, if the manner in which our products are used requires governmental approval or clearance, you must obtain it. Shin-Etsu Silicones, Inc. warrants only that its products will meet its specifications. There is no warranty of merchantability of fitness of use, nor any other expressed or implied warranties. The user's exclusive remedy and Shin-Etsu Silicones, Inc.'s sole liability is limited to refund of the price or replacement of any product shown to be otherwise than as warranted. Shin-Etsu Silicones, Inc. will not be liable for incidental or consequential damages of any kind. Suggestions of uses should not be taken as inducements to infringe any patents.